



YOLKANOL L5TC (NONYLPHENOL ETHOXYLATE FREE)

COMPOSITION :

YOLKANOL L5TC IS LECITHIN BASED FATLIQUOR THAT IS COMPOUNDED TO TO GIVE MAXIMUM SOFTNESS.

YOLKANOL L5TC WOULD PRODUCE VERY SOFT, FLUFFY, SMOOTH, LIGHT, AND PLEASANT FEEL LEATHER.

YOLKANOL L5TC WOULD NOT CAUSE ANY FATTY SPEW DURING WINTER. LEATHER FATLIQUORED WITH YOLKANOL L5TC WILL NOT GIVE ANY GREASY FEEL OR HARD TO FINISHED LEATHER.

APPLICATION :

- A. OPENING OF WRINKLES ALONG NECK AREA OF GOATSKIN, BUFFALO, AND HEAVY BULL HIDES
- B. RETANNING, NEUTRALIZING, AND FATLIQUORING BATH
- C. UPHOLSTERY LEATHER
- D. NAPPA AND GARMENT LEATHER
- E. GLOVING LEATHER
- F. ON SPLIT UPHOLSTERY LEATHER, YOLKANOL L5TC WOULD GIVE VERY SILKY AND EASY TO FINISH SPLITS
- G. USE IN CONJUNCTION WITH ALLODERM BLACK 2B WILL HELP IN SHADE DEEPENING OF BLACK LEATHER.
- H. ON E.I. TANNED LEATHER, L5TC WILL NOT SPEW IN SPITE OF HEAVY DOSAGE (20% SHAVE WEIGHT)

PROPERTIES :

APPEARANCE :	LIGHT BROWN VISCOUS PASTE
ANALYSIS :	pH 5.0 - 6.5
ACTIVE INGREDIENT :	52 - 55 %
STABILITY :	RETANNING, NEUTRALIZING, AND FATLIQUORING BATH.
IONIC CHARGE :	ANIONIC

PACKING : 120 KGS OR 160 KGS IN RECONDITIONED PLASTIC DRUM



YOLKANOL L5TC

P-2

UPHOLSTERY LEATHER :

AFTER RECHROMING :

WASH : 200% WATER 45C 10'X3

PREFATLIQUORING : 200% WATER 45C
1/3 OF YOLKANOL L5TC IN THE RECIPE AND RUN TILL
COMPLETE EXHAUSTION

CHANGE FLOAT : 200% WATER 35C
ADD NEUTRALIZING AGENT
1/3 OF YOLKANOL L5TC IN THE RECIPE
OTHER NEUTRALIZING CHEMICALS IN THE RECIPE
AND RUN WITH OTHER CHEMICAL.

AFTER NEUTRALIZED, WASH : 200% WATER 45C 10'

NEW FLOAT : 200% WATER 45C
RETAN IN NORMAL WAY
1/3 YOLKANOL L5TC AND RUN TILL EXHAUST
FORMIC ACID AS NORMAL

SPLITS VERY SHORT NAPS AND GOOD TENSILE STRENGTH :

WETTING BACK : 200% WATER 35C
3% ALCHEM CSAM RUN TILL SOFT, BEST IS TO
RUN OVER NIGHT

NEXT MORNING :

WASH : 200% WATER 35C 10'

RECHROMING : 200% WATER 35C
2% EUREKANOL 50M 20'
5% CHROME
1.5% ALTAN MS 30'
SODIUM ACETATE TILL pH 4.0 - 4.2

DRAIN AND WASH : 200% WATER 45C 10' X 3

RETANNING, DYEING, AND FATLIQUORING :

100% WATER 35C
RETANNING CHEMICALS 20'
DYESTUFF

4 - 5% YOLKANOL L5TC
4 - 5% LEATHERNOL SCM OR NFS
2% AMMONIA RUN TILL DYE THROUGH
FORMIC ACID

WASH : 200% WATER 25C 10'

PASTE DRY AND CARRY ON AS USUAL

SHOE UPPER :

WETTING BACK : 200% WATER 35C
3% ALCHEM CSAM RUN TILL SOFT, BEST IS TO
RUN OVER NIGHT

NEXT MORNING, WASH : 200% WATER 35C 10'

RECHROMING, NEUTRALIZING, AND RETANNING IN NORMAL WAY:

FATLIQUORING IN NEW FLOAT: 200% WATER 45C
1/2 YOLKANOL L5TC OF TOTAL
1/2 LEATHERNOL UFBW-P OR NFS OF TOTAL
MIX TWO COMPONENTS WELL TOGETHER.
THEN RUN TILL EXHAUST AND FIX WITH FORMIC ACID
WASH, DRY, ETC IN NORMAL WAY