



ALTAN M

COMPOSITION:

ALTAN M IS BASED ON INORGANIC SALT THAT HAS VERY LOW SOLUABILITY IN WATER. DUE TO THIS PROPERTY, ALTAN M WOULD INCREASE THE pH OF TANNING BATH VERY GRADUALLY. (WHICH IS ESSENTIAL FOR TANNING OF VERY SMOOTH AND TIGHT GRAIN LEATHER.)

IN ORDER TO AVOID PATCHY WET BLUES, ALTAN M ONCE ADDED TO THE TANNING BATH, THE TANNING DRUM SHOULD NOT BE STOPPED UNDER ANY CIRCUMSTANCES. IN ORDER TO COMPLETELY UTILIZE ALTAN M, RUNNING TIME OF AT LEAST 10 HOURS IS A MUST, AFTER ADDITION OF ALTAN M TO THE TANNING BATH.

APPLICATION:

- A. BASIFICATION OF CHROME TANNING BATH (0.8-1% ON PELT WEIGHT)
- B. FOR BETTER FIXATION OF CHROME IN THE RECHROMING BATH (0.3-0.5% ON SHAVE WEIGHT, DEPENDED ON THE AMOUNT OF CHROME POWDER USED)
- C. FOR PRODUCTION OF VERY DARK LEATHER, ALTAN M CAN BE USED AS THE MAIN NEUTRALIZING AGENT. (0.2-0.4% ON SHAVE WEIGHT)
- D. FOR BETTER EXHAUSTION OF CHROME IN THE TANNING BATH. (0.8-1% ON PELT WEIGHT)

PROPERTIES:

APPEARANCE: PINKISH WHITE POWDER
ANALYSIS: pH 8.5-9.5 (10% SOLUTION)
ACTIVE INGREDIENT: 99%

PACKING: 30KGS PLASTIC / PAPER BAGS

This information is based on our current state of knowledge and experience and without any obligations on our part.

Technical advice given to customers in written forms or by trials do not absolve the customer, on the account of outside influences which may have an effect on the results of testing or trials.